



SAFETY 2 MIL CLEAR

| | |
|-------------------------------|-----|
| THICKNESS OF FILM (MIL) | 2 |
| % VISIBLE LIGHT TRANSMITTANCE | 87 |
| % VISIBLE LIGHT REFLECTANCE | 9 |
| % SOLAR TRANSMITTANCE | 83 |
| % SOLAR REFLECTANCE | 8 |
| % SOLAR ABSORBANCE | 9 |
| SHADING COEFFICIENT | 0.9 |
| % ULTRA VIOLET TRANSMITTANCE | <2 |
| % TSER | 2 |
| % GLARE REDUCTION | 1 |

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 4 MIL CLEAR

| | |
|-------------------------------|------|
| THICKNESS OF FILM (MIL) | 4 |
| % VISIBLE LIGHT TRANSMITTANCE | 87 |
| % VISIBLE LIGHT REFLECTANCE | 9 |
| % SOLAR TRANSMITTANCE | 79 |
| % SOLAR REFLECTANCE | 8 |
| % SOLAR ABSORBANCE | 13 |
| SHADING COEFFICIENT | 0.96 |
| % ULTRA VIOLET TRANSMITTANCE | <2 |
| % TSER | 2 |
| % GLARE REDUCTION | 1 |

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 7 MIL CLEAR

| | |
|-------------------------------|------|
| THICKNESS OF FILM (MIL) | 7 |
| % VISIBLE LIGHT TRANSMITTANCE | 87 |
| % VISIBLE LIGHT REFLECTANCE | 10 |
| % SOLAR TRANSMITTANCE | 79 |
| % SOLAR REFLECTANCE | 8 |
| % SOLAR ABSORBANCE | 13 |
| SHADING COEFFICIENT | 0.95 |
| % ULTRA VIOLET TRANSMITTANCE | <2 |
| % TSER | 2 |
| % GLARE REDUCTION | 0 |

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



SAFETY 12 MIL CLEAR

| | |
|-------------------------------|------|
| THICKNESS OF FILM (MIL) | 12 |
| % VISIBLE LIGHT TRANSMITTANCE | 87 |
| % VISIBLE LIGHT REFLECTANCE | 10 |
| % SOLAR TRANSMITTANCE | 78 |
| % SOLAR REFLECTANCE | 9 |
| % SOLAR ABSORBANCE | 13 |
| SHADING COEFFICIENT | 0.95 |
| % ULTRA VIOLET TRANSMITTANCE | <2 |
| % TSER | 4 |
| % GLARE REDUCTION | 2 |

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.



UV 2MIL CLEAR

| | |
|-------------------------------|------|
| THICKNESS OF FILM (MIL) | 2 |
| % VISIBLE LIGHT TRANSMITTANCE | 89 |
| % VISIBLE LIGHT REFLECTANCE | 6 |
| % SOLAR TRANSMITTANCE | 81 |
| % SOLAR REFLECTANCE | 6 |
| % SOLAR ABSORBANCE | 13 |
| SHADING COEFFICIENT | 0.98 |
| % ULTRA VIOLET TRANSMITTANCE | <1 |
| % TSER | 15 |
| % GLARE REDUCTION | 2 |

Note: Armolan is a Global Window Film Supplier created through the integration of knowledge, advantage in costs, time and innovation.